

A Review on Composite Materials Reinforcing with Organic/Natural Materials

Dr. S. Arunkumar¹, P. Bharathvaaj², R.K. Mathubalan³, S. Logesh⁴

¹Assistant Professor, Mechanical Engineering, Thiagarajar College of Engineering, Madurai, Tamil Nadu, India.

^{2,3,4}Mechanical Engineering, Thiagarajar college of engineering, Madurai, Tamil Nadu, India.

Email Id: sakmech@tce.edu¹, bharathp561@gmail.com², mathubalan1204@gmail.com³,

logeshss2002@gmail.com⁴

Abstract

The utilization of natural and fiber-reinforced polymer matrix composites as a sustainable solution in the industries. The composite consists of sugarcane bagasse and mesquite fibers. which offers a low-cost, environmentally friendly alternative with potential applications in various industries. epoxy resin known for its cost-effectiveness and resilience, serves as the matrix material. Types of fabrication methods are Vacuum Bag Molding, Hand Lay-Up, Filament Winding, and Hydraulic compression molding from the literature we collected Hydraulic compression molding technique with varying fiber orientations (uniaxial, biaxial, and triaxial) is selected for its versatility and reduced material waste. The study involved alkaline, potassium permanganate, and potassium dichromate treatments. The overall study concludes the promising potential of using bagasse and mesquite fibers as sustainable alternatives for reinforcement in epoxy resin composites, offering a viable solution for valorizing agricultural waste and promoting environmentally conscious manufacturing practices. Chemical treatments and fiber processing play a crucial role in enhancing the properties of the fibers, making them suitable for composite applications.

Keywords: Compression moulding, Bagasse fibers, Mesquite fibers

1. Introduction

The natural and fiber-reinforced polymer matrix composite has many benefits, such as low production costs, low energy consumption, environmental friendliness, and general contribution to achieving sustainable development. This kind of composite has also been a popular research topic in many countries [1,46]. A fiber-reinforced polymer (FRP) is a composite material consisting of a polymer matrix embedded with high-strength fibers, such as glass, aramid and carbon, natural fiber, etc. Reinforced polymer composites (RPC) will have high corrosion resistance, wear resistance, appearance, temperature-dependent behavior, environmental stability, thermal insulation, and conductivity Many types of natural fibers have been investigated for use in plastics including jute, straw, Flax, hemp, wood, sugarcane, bamboo, grass, kenaf, sisal, coir, rice husks, wheat, barley, oats, kapok,

mulberry, banana fiber, raphia, pineapple leaf fiber, and papyrus, etc [2,39,48]. In many areas, lots of landscapes are occupied by Prosopis juliflora(PJ) plants, which makes it difficult to cultivate crops also it absorbs the water and nutrients from the land and makes it unable to cultivate [3,4,47]. A lot of research work is undergoing to use these plants effectively for various applications. Saravanakumar et al analyzed the parameters of the fibers, they found that they had an average microfibril angle of 10.64 and utmost elongation strength of 558 MPa. It was found that the aspect ratio of the PJ fibers had a significant impact on the mechanical qualities of the finished product [5]. The tensile and thermal properties of treated PJ fibers were shown to be superior to those of untreated fibers in a study by Madhu et al [6]. Filler-reinforced epoxy composites can improve mechanical properties by as much as 45

percent, according to research by Santhosh et al., who studied the morphology and properties of PJ and reinforced composites [7]. Natural fibers have gained popularity and are beginning to supplant synthetic fibers, owing to their contribution to sustainable practices. As a result of environmental, social, and economic development, numerous industries have altered their manufacturing processes, materials, and procedures to ensure a sustainable future. While natural fibers have significant disadvantages, they can be overcome with appropriate chemical treatments and fiber processing [8]. Sugarcane bagasse (SCB) is an organic waste generated in the production of sugar and ethanol. It is estimated that for each tonne of sugarcane produced, approximately 300 kg of SCB is generated [9,37]. SCB is classified as a low-cost, low-density, biodegradable, and renewable residue. In the present study, we describe a new approach to reuse SCB and mesquite and form a useful natural composite material.

2. Materials And Methods

2.1 Mesquite Fiber

Prosopis juliflora fiber (Table 1) (PJF), has the potential characteristics to be effectively used as reinforcement materials in the manufacturing of composite applications. Alkaline treatment of PJF will improve cellulose degradation temperature and also density will be increased due to alkaline treatment.[6]. The various physical and chemical treatments help in reducing moisture content in the fibers as well as modifying the mechanical properties, thermal stability, and surface morphology of these fibers [11,36]. Fibers are removed from the bark by utilizing a conventional combing process. [5].

2.2 Sugarcane Bagasse as Reinforcement

The residue after extracting juice from sugarcane is regarded as bagasse. It is estimated more than 200 million tons of sugarcane bagasse are obtained annually in India alone [12,43]. Sugarcane bagasse is approximately composed of 50% cellulose, 25% hemicellulose, and 25% lignin [13,35]. Studies have shown bagasse has a density of 1.28 g/cc and a crystallinity index of about 35%[14]. the tensile

strength is in the range of 20–50 MPa, and the tensile modulus is 2.7 GPa[15]. Sugarcane bagasse like all other natural cellulosic fibers has a natural disadvantage of hydrophilicity which tends to draw moisture from the surroundings resulting in swelling and loss of mechanical properties (Table 2). To some extent, this deficiency of natural fibers could be minimized by modifying them by subjecting them to various chemical treatments [16,38].

Table 1 Properties of Prosopis Juliflora Fiber [10,49]

S. No.	Properties	Prosopis Juliflora Fibre
1	Density (g/cm ³)	0.589
2	Moisture content (wt.%)	8.48
3	Lignin (wt.%)	15.11
4	Cellulose (wt.%)	60.42
5	Hemicelluloses (wt.%)	15.21
6	Wax (wt.%)	0.58
7	Elongation at break (%)	1.55 ± 0.12
8	Tensile strength (MPa)	570 ± 8.4
9	Young's modulus (GPa)	5.87 ± 1.7
10	Diameter (μm)	20

Table 2 Tensile Properties of Bagasse Fiber [17]

Bagasse fibers	Tensile strength (MPa)	Tensile modulus (GPa)
Untreated fibers (Ramleea et al., 2019, Vilay et al., 2008)	20-50, 96	2.7, 6.42
Alkali-treated fibers (Vilay et al., 2008)	156	7.13
Acrylic acid-treated fibers (Vilay et al., 2008)	229	8

2.3 Epoxy

Epoxies have superior mechanical qualities, including increased thermal stability, wear and chemical resistance, and resistance to aging caused by environmental factors [23]. The natural fiber reinforcement in the epoxy matrices results in lower density, weight, and cost, accompanied by better

renewability and biodegradability. physical, mechanical, and thermal properties of natural fiber-reinforced epoxy composite display better performance for manufacturing high-performance automotive and aerospace products and their components [22]. Composition of Bagasse is shown in Table 3.

Table 3 Composition of Bagasse

S. No	COMPOSITION OF BAGASSE	REFERENCE
1	Cellulose 43%, Hemicellulose 10.1%, Lignin 33.23%, ash 1%, Moisture 6.45%	Ibrahim et al[14]
2	Cellulose 40%, Hemicellulose 24.5%, lignin 20%, wax 3.5%, ash 2.4%, silica 2%	Mulinari et al[19]
3	Cellulose 49.44%, hemicellulose 23.19%, Lignin 12.56%, Ash and extractives 14.8%	Ramleea et al[20]
4	Cellulose 36.32%, Hemicellulose 24.7%, lignin 18.14%	Vilay et al[21]
5	Cellulose 35.46%, Hemicellulose 31.25%, lignin 23.7%, ash 9.5%	Kordkheili et al[15]
6	Cellulose 50.4%, Hemicellulose 28.5 %, lignin 14.9%, ash 2%	Xiong et al[18]

3. Extraction of Mesquite

3.1 Water Retting

The water retting process for the extraction of mesquite fibers. Retting is a process of separating fibers in the stem from the woody portion by the action of microorganisms present in the water [24,45]. it is a process in which A glass tank (30 L) filled with 20 L of well water and heated to 28 C

was used to ret nettle stems. The tank should be covered with a transparent glass lid to maintain the water temperature constant. the bark was easily removed from the core by rubbing the stalk with one's fingers. After drying, fibers are mechanically separated [25]

3.2 Alkaline Treatment

Alkaline treatment is a process in which PJFs are treated under concentrations of 6% (w/v) using NaOH solution maintained at room temperature for about 45 min [6].

4. Extraction of Bagasse

4.1 Alkaline Treatment for Bagasse

Alkali treatment reduces the degree of polymerization and minimizes lignin content and hemicellulose from the fiber. Some reports indicate alkaline treatment influences the number of possible reaction sites on the fiber surface and an increase in the surface roughness, both contributing to the enhanced mechanical properties [26]. In this process, extracted sugarcane bagasse fibers are subjected to alkali pretreatment by soaking in aqueous 10% NaOH solution for 3 hours. The soaked bagasse is separated and rinsed with distilled water until a neutral pH is achieved. After rinsing, the fibers should dry for 24 hours [27-30 &42].

4.2 Potassium Permanganate Treatment (KmnO₄)

In this treatment, 1 gm of 10% NaOH pretreated bagasse is taken along with the 10% of 5 mL KMnO₄ in a round bottom flask fitted with a condenser and heated in a water bath for 8 hours. Then wash it with water to attain the neutral pH and further wash it with oxalic acid to remove the MnO₂ impurities. it should dry at last to remove moisture content [31,40].

4.3 Potassium Dichromate Treatment (K₂Cr₂O₇)

This treatment involves taking 1 gm of pretreated bagasse along with 10% of 5 mL K₂Cr₂O₇ solution in a round bottom flask fitted with a condenser and then it should heat in a water bath for 8 hours. Then wash it with water to attain a neutral PH. It is dried to remove moisture content completely [31,41].

4.4 Method

Compression Moulding Process for fabricating naturally Fiber-reinforced Polymer Matrix Composites (PMCs) due to its ability to produce high-quality, uniform parts with excellent mechanical properties [32, 33]. The process offers excellent control over Fiber orientation and alignment, ensuring that the composite material conforms to the desired shape and maintains structural integrity [34-37]. Sugarcane bagasse and mesquite are chopped before combining with epoxy resin in different compositions. Compression test is carried out by a universal testing machine on composite specimens following the ASTM D790 standard [38]. Compression molding enables the consolidation of multiple layers of fiber reinforcement, resulting in a strong and durable composite structure for complex shapes also high pressure applied during compression molding helps to eliminate voids and achieve uniform resin distribution, ensuring consistent mechanical properties throughout the complex shape [39, 43].

Conclusion

The review highlights the promising potential of utilizing bagasse and mesquite fibers as sustainable alternatives for reinforcement in epoxy resin composites [44-46]. This not only addresses the imperative need for valorizing agricultural waste but also fosters a shift towards more environmentally friendly practices in manufacturing. As industries continue to seek sustainable solutions, the examined composite materials and fabrication techniques stand out as viable options, opening avenues for further exploration and adoption in real-world applications [47-49].

Reference

- [1]. Zhanying Sun Progress in the research and applications of natural fiber-reinforced polymer matrix composites doi.org/10.1515/secm-2016-0072 (2017)
- [2]. Groover, M P, Fundamental of Modern Manufacturing, 2nd, ed. John Wiley & Sons, Inc, 111 River Street, Hoboken, NJ, 2004.
- [3]. Wakie, T.T.; Laituri, M.; Evangelista, P.H. Assessing the Distribution, and Impacts of Prosopis Juliflora through Participatory Approaches. Appl. Geogr. 2016, 66, 132–143. [CrossRef]
- [4]. Sato, T. Beyond Water-Intensive Agriculture: Expansion of Prosopis Juliflora and Its Growing Economic Use in Tamil Nadu, India. Land Use Policy 2013, 35, 283–292. [CrossRef]
- [5]. Surya Rajan, B.; Balaji, M.A.S.; Saravanakumar, S.S. Effect of Chemical Treatment and Fiber Loading on Physico-Mechanical Properties of Prosopis Juliflora Fiber Reinforced Hybrid Friction Composite. Mater. Res. Express 2019, 6, 035302. [CrossRef]
- [6]. Madhu, P.; Pradeep, S.; Sanjay, M.R.; Siengchin, S. Characterization of Raw and Alkali Treated Prosopis Juliflora Fibers for Potential Polymer Composite Reinforcement. IOP Conf. Ser. Mater. Sci. Eng. 2019, 653, 012016. [CrossRef]
- [7]. Santhosh, M.S.; Karthikeyan, G.; Sasikumar, R.; Hariharan, R.; Mohanraj, R. Mechanical and Morphological Behaviour of Rice Husk/Prosopis Juliflora Reinforced Bio Composites. Mater. Today Proc. 2020, 27, 556–560. [CrossRef]
- [8]. Azman, M.A.; Asyraf, M.R.M.; Khalina, A.; Petr °u, M.; Ruzaidi, C.M.; Sapuan, S.M.; Wan Nik, W.B.; Ishak, M.R.; Ilyas, R.A.; Suriani, M.J. Natural Fiber Reinforced Composite Material for Product Design: A Short Review. Polymers 2021, 13, 1917. [CrossRef]
- [9]. Silva DC, Melo CA, Junior FHS, Moreira AB, Ferreira OP, Bisinoti MC (2017) Effect of the reaction medium on the immobilization of nutrients in hydrochars obtained using sugarcane industry residues. Biores Technol 237:213–221
- [10]. S. R. Benin, S. Kannan, A. Jacob Moses, et al., Mechanical characterization of Prosopis juliflora reinforced polymer matrix composites with filler material

- [11]. Reddy KO, Ashok B, Reddy KR, Feng YE, Zhang J, Rajulu AV. Extraction and characterization of novel lignocellulosic fibers from *Thespesia lampas* plant. *International Journal of Polymer Analysis and Characterization*. 2014 Jan 31;19(1):48-61.
- [12]. Almazan, O., Gonzalez, L., & Galvez, L. (2001). The sugarcane, its byproducts, and co-products. *Sugarcane International*, 3–8.
- [13]. Aigbodion, V. S., Hassan, S. B., & Agunsoye, J. O. (2012). Effect of bagasse ash reinforcement on dry sliding wear behaviour of polymer matrix composites. *Materials & Design*, 33, 322–327. <https://doi.org/10.1016/j.matdes.2011.07.002>
- [14]. Ibrahim, M. I. J., Sapuan, S. M., Zainudin, E. S., & Zuhri, M. Y. M. (2020). Preparation and characterization of cornhusk/sugar palm fiber reinforced Cornstarch-based hybrid composites. *Journal of Materials Research & Technology*, 9(1), 200–211. <https://doi.org/10.1016/j.jmrt.2019.10.045>
- [15]. Kordkheili, H. Y., Hizioglu, S., & Farsi, M. (2012). Some of the physical and mechanical properties of cement composites are manufactured from carbon nanotubes and bagasse fiber. *Materials & Design*, 33, 395–398. <https://doi.org/10.1016/j.matdes.2011.04.027>
- [16]. Karp, S. G., Woiciechowski, A. L., Soccol, V. T., & Soccol, C. R. (2013). Pretreatment Strategies for delignification of Sugarcane bagasse: A review. *Brazilian Archives of Biology and Technology*, 56(4), 679–689. <https://doi.org/10.1590/S1516-89132013000400019>
- [17]. Devadiga et al., *Cogent Engineering* (2020), 7: 1823159 <https://doi.org/10.1080/23311916.2020.1823159>
- [18]. Xiong, W. (2018). Bagasse composites: A review of material preparation, attributes, and affecting factors. *Journal of Thermoplastic Composite Materials*, 31(8), 1112–1146. <https://doi.org/10.1177/0892705717734596>
- [19]. Mulinari, D. R., Voorwald, H. J. C., Cioffi, M. O. H., Da Silva, M. L. C. P., Da Cruz, T. G., & Saron, C. (2009). Sugarcane bagasse cellulose/HDPE composites obtained by extrusion. *Composites Science and Technology*, 69(2), 214–219. <https://doi.org/10.1016/j.compscitech.2007.10.005>
- [20]. Ramleea, N. A., Jawaid, M., Zainudin, E. S., & Yamani, S. A. K. (2019). Tensile, physical and morphological properties of oil palm empty fruit bunch/ sugarcane bagasse fiber reinforced phenolic hybrid composites. *Journal of Materials Research and Technology*, 8(4), 3466–3474. <https://doi.org/10.1016/j.jmrt.2019.06.016>
- [21]. Vilay, V., Mariatti, M., Mat Taib, R., & Todo, M. (2008). Effect of fiber surface treatment and fiber loading on the properties of bagasse fiber-reinforced unsaturated polyester composites. *Composites Science and Technology*, 68(3–4), 631–638. <https://doi.org/10.1016/j.compscitech.2007.10.005>
- [22]. Naheed Saba, Mohammad Jawaid Azman Hassan Recent advances in epoxy resin, natural fiber-reinforced epoxy composites and their applications (2015) DOI: 10.1177/0731684415618459
- [23]. Sienkiewicz, N.; Dominic, M.; Parameswaranpillai, J. Natural Fillers as Potential Modifying Agents for Epoxy Composition: A Review. *Polymers* 2022, 14, 265.
- [24]. T. Krishnan, S. Jayabal & V. Naveen Krishna (2018): Tensile, flexural, impact, and hardness properties of alkaline-treated Sunnhemp fiber reinforced polyester composites, *Journal of Natural Fibers*, DOI: 10.1080/15440478.2018.1492488
- [25]. Laura Bacci, Sara Di Lonardo, Lorenzo Albanese, Giorgio Mastromei, and Brunella

- Perito, Effect of different extraction methods on fiber quality of nettle (*Urtica dioica* L.) T Research Journal 81 (8) 827–837.
- [26]. Bam, S. A., Gundu, D. T., & Onu, F. A. (2019). The effect of chemical treatments on the mechanical and physical properties of bagasse filler reinforced low density polyethylene composite. *American Journal of Engineering Research*, 8(4), 95–98. <http://www.ajer.org/papers/Vol-8-issue-4/K08049598.pdf>
- [27]. Cao, Y., Shibata, S., & Fukumoto, I. (2006). Mechanical properties of biodegradable composites reinforced with bagasse fiber before and after alkali treatments. *Composites Part A: Applied Science and Manufacturing*, 37, 423–429. doi:10.1016/j.compositesa.2005.05.045
- [28]. Rajasekaran, T., & Gokul, K. (2016). Evaluation of mechanical characteristics of treated and untreated sugarcane fiber composites. *Journal of Chemical and Pharmaceutical Sciences*, 9, 652–656.
- [29]. Simaoa, J. A., Carmonaa, V. B., Marconcinia, J. M., Mattosoa, L. H. C., Barsberg, S. T., & Sanadi, A. R. (2016). Effect of fiber treatment condition and coupling agent on the mechanical and thermal properties in highly filled composites of sugarcane bagasse Fiber/PP. *Materials Research*, 19, 746–751. doi:10.1590/1980-5373-MR-2015-0609
- [30]. Vilay, V., Mariatti, M., Taib, R. M., & Todo, M. (2007). Effect of fiber surface treatment and fiber loading on the properties of bagasse fiber–Reinforced unsaturated polyester composites. *Composites Science and Technology*, 68, 631–663. doi:10.1016/j.compscitech.2007.10.005
- [31]. Roopa Prabhu, Sharad Ganesh, GT Mahesha & K Subrahmanya Bhat | (2022) Physicochemical characteristics of chemically treated bagasse fibers, *Cogent Engineering*, 9:1, 2014025, DOI: 10.1080/23311916.2021.2014025
- [32]. Temesgen Berhanu Yallew, Eshetie Kassegn, Sirak Aregawi, Alula Gebresias (2020) Study on the effect of process parameters on tensile properties of compression molded natural fiber reinforced polymer composites, DOI: 10.1007/s42452-020-2101-1
- [33]. S. Krishna Mohan, Arul Thayammal Ganesan, M. Ramarao, Amol L. Mangrulkar, S. Rajesh, Sami Al Obaid, Saleh Alfarraj, S. Sivakumar, and Manikandan Ganesan (2021) Evaluation of Mechanical Properties of Sisal and Bamboo Fibers Reinforced with Polymer Matrix Composites Prepared by Compression Moulding Process DOI: 10.1155/2021/2832149
- [34]. Jiuming Xie, Jin Wu and Xuejun Zhou (2020) Research on Compression Molding Process of Carbon Fiber Reinforced Polymer DOI:10.1088/1755-1315/693/1/012067
- [35]. DG Devadiga, KS Bhat, GT Mahesha 2020 Sugarcane bagasse fiber reinforced composites DOI: 10.1080/23311916.2020.1823159.
- [36]. Maya Jacob, Sabu Thomas, Sakthi Ganapathy, Aravind Sakthive, Mohamed Thariq Hameed Sultan 2022 Effect of Prosopis Juliflora Thorns on Mechanical Properties of Plastic Waste Reinforced Epoxy Composites DOI: doi.org/10.3390/polym14071278
- [37]. Vijaykumar Guna a b, Manikandan Ilangovan c, Chunyan Hu d e, Krishna Venkatesh a, Narendra Reddy 2019 Valorization of sugarcane bagasse by developing completely biodegradable composites for industrial applications DOI: 10.1016/j.indcrop.2019.01.011.
- [38]. Waqas Ahmad a, Ayaz Ahmad a b, Krzysztof Adam Ostrowski b, Fahid Aslam c, Panuwat Joyklad d, Paulina Zajdel 2021 Sustainable approach of using sugarcane bagasse ash in cement-based composites: A

- systematic review DOI:
10.1016/j.cscm.2021.e00698
- [39]. Mohd. Khalid Zafeer, Roopa Prabhu, Sithara Rao, GT Mahesha & K Subrahmanya Bhat 2023 Mechanical Characteristics of Sugarcane Bagasse Fiber Reinforced Polymer Composites: A Review DOI: <https://doi.org/10.1080/23311916.2020.1823159>
- [40]. Roopa Prabhu, Sharad Ganesh, GT Mahesha ORCID Icon & K Subrahmanya Bhat 2021 Physicochemical characteristics of chemically treated bagasse fibers doi.org/10.1080/23311916.2021.2014025
- [41]. V. Vidyashri, Henrita Lewis, P. Narayanasamy ORCID Icon, G T Mahesha & K. Subrahmanya Bhat 2019 Preparation of chemically treated sugarcane bagasse fiber reinforced epoxy composites and their characterization DOI: [10.1080/23311916.2019.1708644](https://doi.org/10.1080/23311916.2019.1708644)
- [42]. Fábio Friol Guedes de Paiva, Vitor Peixoto Kliench de Maria, Giovani Barrera Torres, Guilherme Dognani, Renivaldo José dos Santos, Flávio Camargo Cabrera & Aldo Eloizo Job 2018 Sugarcane bagasse fiber as semi-reinforcement filler in natural rubber composite sandals DOI: [10.1007/s10163-018-0801-y](https://doi.org/10.1007/s10163-018-0801-y).
- [43]. Francisco Hernández-Olivares a, Rosa Elizabeth Medina-Alvarado b, Xavier Eduardo Burneo-Valdivieso b, Alonso Rodrigo Zúñiga-Suárez c 2020 Short sugarcane bagasse fibers cementitious composites for building construction DOI: [10.1016/j.conbuildmat.2020.118451](https://doi.org/10.1016/j.conbuildmat.2020.118451).
- [44]. Javier Osés a, Mayra Fabregat-Vázquez b, Ruth Pedroza-Islas b, Sergio A. Tomás c, Alfredo Cruz-Orea c, Juan I. Maté 2010 Development and characterization of composite edible films based on whey protein isolate and mesquite gum [10.1016/j.jfoodeng.2012.03.006](https://doi.org/10.1016/j.jfoodeng.2012.03.006).
- [45]. Howayda M. Mohammed, Taiseer Hassan M., Ahmed A. A. Youssif Production of Fiber From Mesquite Plant (2019)
- [46]. 46.D.N. Saheb, J.P. Jog, Natural fiber polymer composites: A review, *Adv. Polym. Tech.* 18 (4) (1999) 351–363.
- [47]. A.N. Netravali, S. Chabba, Composites get greener, *Mater. Today* 6 (4) (2003) 22–29.
- [48]. K.P. Kumar, A.S.J. Sekaran, Some natural fibers used in polymer composites and their extraction processes: a review, *J. Reinf. Plast. Compos.* 33 (20) (2014) 1879–1892.
- [49]. Rennan Pereira de Gusmao~*, Mario Eduardo Rangel Moreira Cavalcanti-Mata, Maria Elita Martins Duarte, Thaisa Abrantes Souza Gusmao Particle size, morphological, rheological, physicochemical characterization and designation of minerals in mesquite flour (*Proposis juliflora*)(2016)